

UV FOG 702BL

Product Description

Hernon® UV FOG (Form on Gasket) 702BL is an EB/UV curable product that provides excellent adhesion to shaft seals, oil seals, metals, glass, ceramics and plastics. Can be used as a Form-in-place gasket in oil and coolant systems. Typical applications include Engine covers, Oil pans and other fluid seal systems.

Typical Properties (Uncured)

Property	Value
Appearance	Blue
Viscosity @ 25°C, cP	700 to 900
Tack Free Time, seconds	≤ 5
Refractive Index	1.489
Density (ASTM D1475)	8.92 lb/gal
Flash Point	See SDS

Typical Properties (Cured)

Property	Value
Hardness, Shore A	10 to 25
Temperature Range, °F (°C)	-40 to 302 (-40 to 150)
Gap fill	0.1 up to 1.0 mm

Tack Free Time

Measured @ 365 nm, using medium pressure, mercury arc lamp: US 1000, at ½ inch distance: < 5 seconds
By using LED9, at ¼ inch distance: < 12 seconds

Block Shear Strength

Cured 24 Hours at 22°C
Tested according to ASTM D4501

Substrate	Value (psi)
Glass to Glass	≥100
Glass to Steel	≥100

Fluid Compatibility

Cured for 1 day at RT.
Initial hardness (shore A): 65
Cured Material aged under condition indicated.
Tested at RT.

Hardness Shore M ¹ Fluids Tested	Temp (°C)	Hardness after			
		72 h	168 h	540h	1008 h
Dexron VI ATF ¹	150	70	70	73	76

¹ Third party tested

Fluids	Temp (°C)	Hardness (Shore A)
		1008 h
Dexron VI ATF	150	97
CVT Fluid	150	80
Pentosin Motor oil	120	68
Synthetic Motor Oil	120	73
Gear Oil	120	94

Storage

UV Fog 702BL can be stored in a dry location in unopened containers at a temperature between 60°F to 90°F (15°C to 32°C) unless otherwise labeled. Material must be mixed and heated to 80 – 90 °F (26 – 32°C) prior to use. Avoid direct exposure to sunlight or fluorescent lighting. To prevent contamination of unused material, do not return any material to its original container.

Cured Seals Shelf life

Seals can be stored for a minimum of 3 years at Room Temperature.

Cleanup

Uncured **UV Fog 702BL** should be cleaned up with absorbent material and placed in a closed container for disposal. Small areas can be cleaned up by curing the product prior to disposal by exposing the product to UV cure, light or sunlight. Afterwards the area can be washed with soap and water.

Dispensing Equipment

Hernon® offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Hernon® Technical Data Sheet

UV FOG 702BL

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING®, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard