

## Copper Based Anti-Seize 367

### Product Description

**Hernon® Copper Based Anti-Seize 367** is a low-friction, anti-seize lubricant manufactured from a combination of micro-size copper flakes and graphite dispersed in a water-resistant grease and fortified with antioxidants, plus rust and corrosion inhibitors.

**Copper Based Anti-Seize 367** provides a shield against metal-to-metal contact, preventing seizure and corrosion. It fills irregularities and imperfections and resists welding, hardening, or setting. Provides low friction and cushions impact and shock loads. Low shear between particles reduces stick-slip, allowing quick disassembly with minimum wrench torque. It will not squeeze out of the threads, gum up, or wash off.

### Product Benefits

- Conforms to MIL-PRF-907F
- Conforms to Raytheon spec M8656839 Type I
- Service rating: -65°F (-54°C) to 1800°F (982°C).
- Contains no lead or zinc.
- Water Resistant
- Lowers friction; reduces wrench torque.
- Permits reuse of fittings; saves stud, bolt, and nut replacement.
- Not affected by contraction, expansion, or vibration.
- Will not run, drip, or settle out.

### Storage

**Copper Based Anti-Seize 367** should be stored in a cool, dry location in unopened containers at a temperature between 45°F to 85°F (7°C to 29°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

### Typical Applications

is ideal for use on threaded connections, pump housings, flanges, studs, exhaust manifold bolts, compressor heads, autoclaves, lathe centers, etc.

### Typical Properties

Property	Value
Thickener	Complex Based
Fluid Type	Petroleum
Dropping Point, ASTM D566	450°F (232°C)
Specific gravity	1.15
Density (lb/gal)	10.1
Solids content % wt	> 35
Tramp elements, % weight	< 20
Particle size, microns	< 50
Torque coefficient K (Nut-factor)	0.15
Oil Separation, ASTM D6184 Wt. % Loss @ 212°F (100°C)	< 3.0 %
Penetration @ 77°F ASTM D217	310 to 330
Copper Strip Corrosion ASTM D-4048	1A
Water Spray Off ASTM D-4049	<10%
Flash point	>450°F (232°C)

### General Information

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

### Dispensing Equipment

**Hernon®** offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING®, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO9001 Quality Standard.