

Quantum® 73421

Product Description

Heron® Quantum® 73421 is a state-of-the-art, single component, solventless, room temperature curing cyanoacrylate adhesive that polymerizes rapidly when pressed into a thin film between parts. The presence of surface moisture commences the cure of the adhesive. **Quantum® 73421** develops handling strength within seconds and full functional strength in a few hours. **Quantum® 73421** can bond a wide variety of surfaces including metals, thermoplastics, elastomers, ceramics, leather, cork, and paper, but is particularly suited for bonding hard-to-bond plastics. Notwithstanding the superior bonding capability of **Quantum® 73421**, it is NOT recommended for long-term glass to glass bonding applications.

Typical Applications

Bonding

Rubber bumpers
Permanent locking of plastic
Fasteners
Speaker components
Shock mounts
Gears to shaft
Wiper blades
Acrylic windows
Nameplates
Catheters
Honing stones
Security collars
O-rings
Insulation pads

Fixturing

Filter caps
Jumper wires
Heat sinks
Gaskets
Golf club parts
Tennis racquet parts
P.C. boards
Wire tacking

Potting

Transistors
Tamper-proofing
Adjustable components
Fiberglass molds

Product Benefits

- Rapid Cure - forms a strong bond at room temperature in less than a minute with contact pressure.
- Surfaces - will bond almost any combination of similar or dissimilar materials.
- Easy Use - single component feature, eliminates any mixing.

Performance Requirements

Quantum® 73421 meets the requirements of MIL-A-46050C, Type II Class 2 and CID A-A-3097 Type II Class 2.

Typical Properties (Uncured)

Property	Value
Chemical Type	Ethyl Cyanoacrylate
Appearance	Clear liquid
Viscosity @ 77°F (25°C), cP	80-200
Specific gravity	1.04
Flash point	See SDS

Typical Properties (Cured)

Cured 24 Hours @ 22°C

Physical Properties

Property	Value
Temperature range, °C, (°F)	-40 to 100 (-40 to 212)

Typical Curing Performance

Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The table below shows the fixture time achieved on different materials at 22°C / 50% relative humidity. Fixture time is defined as the time to develop shear strength of 0.1 N/mm².

Substrate	Fixture Time (seconds)
Steel	< 20
Aluminum	< 30
Buna Rubber	< 15
Polycarbonate	5 -10
Zinc Dichromate	< 240
Neoprene	< 5
ABS	< 30
PVC	< 45
Phenolic	< 30
EPDM	< 5
Balsa Wood	< 5

Cure Speed vs. Bond Gap

The rate of cure will depend on the bond line gap. Thin bond lines result in high cure speeds, increasing the bond gap will decrease the rate of cure.

Cure Speed vs. Accelerator

Where cure speed is unacceptably long due to large gaps, applying accelerator to the surface will improve cure speed. However, this can reduce ultimate strength of the bond and therefore testing is recommended to confirm effect.

Heron® Technical Data Sheet

Quantum® 73421

Typical Cured Performance

Shear Strength

Cured 24 Hours @ 22°C - tested according to ASTM D1002.

Substrate	Shear Strength (psi)
Steel (grit blasted)	≥13.7 (≥ 2000)
Aluminum (grit blasted)	≥13.7 (≥ 2000)
Zinc Dichromate	≥6.8 (≥ 1000)
ABS*	≥3.4 (≥ 500)
PVC*	≥4.1 (≥ 600)
Polycarbonate	≥6.8 (≥ 1000)

*Substrate failure

Block-Shear Strength

Cured 24 Hours @ 22°C - tested according to ASTM D4501

Substrate	Shear Strength (psi)
Phenolic	≥ 1000
ABS	≥ 1000

Tensile Strength

Tested according to ASTM D412

Substrate	Cure Time At 22°C	Tensile Strength N/mm ² (psi)
Buna-N	24 hours	≥ 6.89 (≥ 1000)
EPDM	24 hours	≥ 4.82 (≥ 700)
Neoprene	24 hours	≥ 13.59 (≥ 2000)

Tested according to ASTM D2095

Substrate	Cure Time @ 22°C	Tensile Strength N/mm ² (psi)
Steel	24 hours	≥ 10.34 (≥ 1500)

Typical Environmental Resistance

Cured for 1 week @ 22°C


Shear Strength, ASTM D1002

Steel lap-shear specimens (grit blasted)

Substrate	Shear Strength (psi)
Steel (grit blasted)	≥20.7 (≥ 3000)

Hot Strength

Tested at temperature



Heat Aging

Aged at temperature indicated and tested at 22°C

Temperature	Exposure Time	Shear Strength N/mm ² (psi)
100 °C	1000 hours	≥ 2.7 (400)

Chemical/Solvent Resistance

Aged under condition indicated - Tested at 72°F (22°C).

Chemical/Solvent	Temp (°C)	% of Initial Strength		
		100h	500h	1000h
Motor Oil	40	83	82	82
Gasoline	22	86	86	49
Ethanol	22	90	78	60
Isopropanol	22	95	92	90
Heat / 95% RH	40	51	36	38

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for Use

For best performance bond surfaces should be clean and free from grease. This product performs best in thin bond gaps (0.05 mm).

Disassembly and Cleanup

Liquid Cyanoacrylate should not be wiped with rags or tissue. The fabric will cause polymerization and large quantities of adhesive will heat or cure causing smoke and strong irritating vapors. Always flood with excess water to clean up spill conditions.

Hernon® Technical Data Sheet

Quantum® 73421

Storage

Cyanoacrylate adhesives must be stored under refrigeration at a temperature of 40°F ± 5°F for extended shelf life. Before opening, the containers must be warmed to room temperature - otherwise, water may condense into the bottle and cause hardening of the adhesive. To prevent contamination of unused adhesive, do not return product to its original container.

Dispensing Equipment

Hernon® offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING®, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO9001 Quality Standard.