

EST. 1978 TECHNICAL DATA SHEET ISO-9001

Quantum® 124

Product Description

Hernon® Quantum® 124 is a surface insensitive cyanoacrylate adhesive formulated to improve adhesion properties and fixture time as well as gap filling capabilities over conventional cyanoacrylate adhesives. This advanced formulation improves adhesion to difficult to bond plastics, wood, leather, ceramics, elastomers, and acidic surfaces such as freshly plated components. Quantum[®] 124 is a state-of-art single component, solventless, room temperature curing adhesives that polymerize rapidly when pressed into a thin film between parts. The presence of surface moisture commences the cure of the adhesive. Quantum® 124 will develop handling strength within seconds and full cure within a few hours.

Typical Applications

Bonding

Rubber bumpers Permanent locking of plastic

Fasteners

Speaker components

Shock mounts Gears to shaft Wiper blades Acrylic windows

Name plates Catheters Honing stones

Security collars O-rinas

insulation pads

Fixturing

Filter caps Jumper wires Heat sinks Gaskets Golf club parts Tennis racquet parts P.C. boards Wire tacking

Potting

Transistors Tamper proofing Adjustable components Fiberglass molds

Product Benefits

- Single component.
- 100% Solventless.
- Instant setting.
- Improved gap filling capability.
- Improved adhesion to difficult to bond surfaces

Performance Requirements

Quantum® 124 meets the requirements of MIL-A-46050C, Type II Class 1, and CID A-A-3097 Type II Class 1.

Typical Properties (Uncured)

Property	Value
Chemical Type	Ethyl Cyanoacrylate
Appearance	Clear Liquid
Specific Gravity	1.10
Viscosity, cP	25-35
Flash Point	See SDS
Temperature range, °C (°F)	-55 to 82 (-65 to 180)

Typical Curing Performance

Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The table below shows the fixture time achieved on different materials at 22°C. Fixture time is defined as the time to develop a shear strength of 0.1 N/mm².

Substrate	Fixture (seconds)
Phenolic	≤ 40

Cure Speed vs. Bond Gap

The rate of cure will depend on the bondline gap. Thin bond lines result in high cure speeds, increasing the bond gap will decrease the rate of cure.

Cure Speed vs. Accelerator

Where cure speed is unacceptably long due to large gaps, applying accelerator to the surface will improve cure speed. However, this can reduce ultimate strength of the bond and therefore testing is recommended to confirm effect

Typical Cured Performance

Shear Strength

Cured 24 Hours @ 22°C - tested according to ISO 4587.

Substrate	Shear Strength N/mm² (psi)
Steel (grit-blasted)	≥ 2000

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for Use

For best performance bond surfaces should be clean and free from grease. This product performs best in thin bond gaps (0.05 mm).

Disassembly and Cleanup

Liquid Cyanoacrylate should not be wiped with rags or tissue. The fabric will cause polymerization and large quantities of adhesive will heat or cure causing smoke and strong irritating vapors. Always flood with excess water to clean up spill conditions.

Storage

Cyanoacrylate adhesives must be stored under refrigeration at a temperature of $40^{\circ}\text{F} \pm 5^{\circ}\text{F}$ for extended shelf life. Before opening, the containers must be warmed to room temperature, otherwise, water may condense into the bottle and cause hardening of the adhesive. To prevent contamination of unused adhesive, do not return product to its original container.

Dispensing Equipment

Hernon[®] offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon**[®] **Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.